



MCA Emmecia S.p.a.

20821 meda (MB)
via indipendenza, 131
tel 0362 341987 r.a.
Fax 0362 340431
info@emmecia.it
www.emmecia.it

cap. soc. €2.186.100 i.v.
trib. di monza reg. soc. n.25581
p.iva 00679580969 c.f. 01174990133
c.c.i.a.a. milano n. 1139984

TECHNICAL CHAT

Item Code	M012
Composition	38%VI 37%CO 20%PL 5%PC
Colours	11
Width	138 CM
Fabric Weight per Metre	850,00 GR/ML

COLOUR SHADES MAY SLIGHTLY VARY FROM DYE-LOT TO DYE

TEST	RESULT
RESISTANCE TO ABRASION - Martindal Method UNI EN ISO 12974-2/2000	15.000 rubs
COLOUR FASTNESS WET AND DRY RUBBING (FRICTION) -Method UNI EN ISO 105 X 12:2001	dry: 2-3 wet: 3-4
COLOUR FASTNESS TO ARTIFICIAL LIGHT - Method UNI EN ISO 105 B02/04 - A1 (Marzo 2002)	4-5
PILLING - Method ISO 12945.2	4



MILANO TESSUTI