



MCA Emmezia S.p.a.

20821 meda (MB)
via indipendenza, 131
tel 0362 341987 r.a.
Fax 0362 340431
info@emmezia.it
www.emmezia.it

cap. soc. €2.186.100 i.v.
trib. di monza reg. soc. n.25581
p.iva 00679580969 c.f. 01174990133
c.c.i.a.a. milano n. 1139984

TECHNICAL DETAILS

Item Code	M061
Composition	PILE: 100% RAYON TOT. COMP.: 54%VI 35%CO 11%PL
Colours	
Width	138 CM
Fabric Weight per Metre	670,00 GR/ML

COLOUR SHADES MAY SLIGHTLY VARY FROM DYE-LOT TO DYE

TEST	RESULT
RESISTANCE TO ABRASION - Martindal Method UNI EN ISO 12974-2/2000	20.000 rubs
COLOUR FASTNESS WET AND DRY RUBBING (FRICTION) -Method UNI EN ISO 105 X 12:2001	dry: 4-5 wet: 4
TEAR STRENGTH - Method UNI ISO 13937-1	>20 N
COLOUR FASTNESS TO ARTIFICIAL LIGHT - Method UNI EN ISO 105 B02/04 - A1 (Marzo 2002)	5
TENSILE STRENGTH - Method UNI EN ISO 13934-1	>350 N
SEAM SLIPPAGE - Method ISO 13936-2	warp/weft: 3,00 mm
FIRE RETARDANT	Cigarette Test BS 5852-1 Butane Flame BS 5852-1



MILANO TESSUTI